

PRODUCT DATA

DACFILL MESH

DESCRIPTION

Polyester fibres woven in hexagonal meshes.

RECOMMENDED USES

Reinforcement of the first coat of Dacfill for the system Dacfill-Waterproofing.

TECHNICAL DATA (according to the data given by the manufacturer)

Composition	:	100% polyester fibres
Quality	:	Flexible
Weight	:	48 - 52 g/m ²
Thickness	:	0,28 - 0,29 mm
Traction force in N/5 cm	By warp	: ± 140
	By weft	: ± 95
GRAB elongation in %	By warp	: ± 29
	By weft	: ± 260
Resistance to	UV	: Good - behind glass 7 to 10 years
	Temperature	: Good
	Acids	: In 50% of sulphuric acid - room temperature - 6 months.
	Alkali	: Good - only the surface of the fibres will be attacked at room temperature.
Thermal retraction at 40°C	By warp	: ± 3
	By weft	: ± 1,7%
Dimensions	Widths	: 20 cm, 60 cm en 100 cm
	Roll length	: 100 m
Tolerances	Width	: None
	Length	: - 0 m + 1 m

Rust-Oleum Netherlands B.V.
Braak 1, 4704 RJ
P.O. Box 138, 4700 AC
Roosendaal, The Netherlands
T +31 (0)165 593 636
F +31 (0)165 593 600
info@rust-oleum.eu
www.rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Halen, Belgium
T +32 (0)13 460 200
F +32 (0)13 460 201
info.be@ro-m.com
www.ro-m.com

Rust-Oleum France S.A.S
11, Rue Jules Verne, B.P. 60039
95322 St-Leu-la-Forêt Cedex
France
T +33 (0)1 30 40 00 44
F +33 (0)1 30 40 99 80
info.fr@ro-m.com
www.ro-m.com

Rust-Oleum UK Ltd.
Rotterdam House
116 Quayside
Newcastle
NE1 3DY
United Kingdom
T +44 (0)2476 717 329
F +44 (0)2476 718 930
info@rust-oleum.eu
www.rust-oleum.eu