



Guard Vinyl

Description: A single pack semi-gloss paint with good water and chemical resistance and excellent adhesion.

Uses: Designed for the protection of new galvanised steel structures in atmospheric exposure conditions. Typical applications include gates, railings and general industrial plant.

Pack Sizes:	Colours:	Thinner:
5 Litre	Black – others available upon request.	Guard Standard Thinner

Theoretical Spreading Rate: 4m² per litre

Volume Solids: 30%

Dry Film Thickness (DFT): 75µm

Wet Film Thickness (WFT): 250µm

Flash Point: Above 21° C

VOC Content: 575 gms p/l

Surface Preparation:

Ensure surfaces are clean, dry and free from grease and other contamination before coating. Thoroughly degrease and where applicable, abrade to remove rust and promote good adhesion of the coating. Complex structures may be more effectively cleaned by detergent pressure washing or steam cleaning.

For optimum corrosion protection, mild steel should be blast cleaned to ISO Sa2.5

Mixing Instructions:

It is essential that the material is thoroughly mixed before use.

Application:

Brush <input checked="" type="checkbox"/>	Roller <input checked="" type="checkbox"/>	Airless Spray <input checked="" type="checkbox"/>	Conventional Spray <input checked="" type="checkbox"/>
		Thin if required	Thin as necessary

In order to achieve the recommended dft, additional coats may be required depending on the equipment used, spraying techniques and substrate profile.

Drying Times:

Please note drying times are based on temperature at 20°C.

Touch Dry:

1 hour

Recoatable:

After 3 hours

Hard Dry:

24 hours

Storage:

Keep material in containers and use within 12 months of delivery. Materials not used should be resealed. Store in a cool, dry place and at temperatures no lower than 10°C.

Precautions:

Materials are both hazardous and flammable and therefore precaution measures should be taken and appropriate P.P.E worn in accordance with the Material Safety Data Sheets and regulations.

Health & Safety:

Please view the product Health & Safety Sheet for information in relation to hazardous identification, first aid measures, fire fighting, accidental release, handling, exposure control, personal protective equipment (P.P.E), disposal and regulatory information.

Additional Info:

The above information should be used as a guide only and is not a guarantee or warranty. New Guard Coatings and our supply partners have provided this information in good faith and is to the best of our knowledge correct at the time of print. 'Guard' is a brand owned by New Guard Coatings Ltd, but this does not imply the manufacture of such product.

Review:

Date of Print: March 2014
Last Review: October 2013

Contact Information:

UK Head Office:

New Guard Coatings Ltd
Sandbeck Way, Wetherby, West Yorkshire, LS22 7DN

Tel: +44 (0)1937 586311

Email: uksales@newguardcoatings.com

USA Head Office:

New Guard Coatings Inc
615 South Dupont Highway, Dover, DE, 19901

Tel: +1 (302)-257-5760

Email: usasales@newguardcoatings.com

www.newguardcoatings.com